

area collection

superficie naturale,
5 formati - **5** colori

natural surface - 5 sizes - 5 colours

natur-unpoliert Oberfläche - 5 Formate - 5 Farben


surface naturelle - 5 formats - 5 couleurs

superficie natural - 5 formatos - 5 colores


Натуральная поверхность - 5 форматов - 5 цветов




Pietra arria



Pietra serena




Pietra lavica



Pietra etrusca



Pietra imperiale





pietra imperiale AR 05

Pietra Imperiale AR 05 NAT - 60x120 / 24"x48" + 60x60 / 24"x24"
Mattoncino 5 NAT - 30x30 / 12"x12" + Bacchetta alluminio - 1x60 / 3/8"x24"



pietra serena AR 02
 Pietra Serena AR 02 NAT - 60x60 / 24"x24"
 Mattoncino 2 NAT - 30x30 / 12"x12"



pietra etrusca AR 04
 Pietra Etrusca AR 04 NAT - 30x60 / 12"x24"
 Sixty 4 NAT - 6x30 / 2 2/5"x24" + Insert 4 NAT - 60x60 / 24"x24"
 Ang_Insert 4 NAT - 60x60 / 24"x24" + Inserto vetro tessuto



pietra arria AR 01
 Pietra Etrusca AR 04 NAT - 60x60 / 24"x24"
 Pietra Arria AR 01 NAT - 30x60 / 12"x24" + 60x60 / 24"x24"
 + Insert 1 NAT - 60x60 / 24"x24" + Ang_Insert 1 NAT - 60x60 / 24"x24"
 + Mattoncino 1 NAT - 30x30 / 12"x12" + Inserto vetro trasparente opaco





Pietra arria AR 01 NAT SQ
60x60x1,05 / 24"x24"x¹/₂"



Pietra arria AR 01 NAT SQ
30x60x1,05 / 12"x24"x¹/₂"



Pietra arria AR 01 NAT SQ
45x45x1,05 / 18"x18"x¹/₂"



Pietra serena AR 02 NAT SQ
60x120x1,2 / 24"x48"x¹/₂"



Pietra serena AR 02 NAT SQ
30x120x1,2 / 12"x48"x¹/₂"




Pietra serena AR 02 NAT SQ
60x60x1,05 / 24"x24"x¹/₂"




Pietra serena AR 02 NAT SQ
30x60x1,05 / 12"x24"x¹/₂"



Pietra serena AR 02 NAT SQ
45x45x1,05 / 18"x18"x¹/₂"



Pietra lavica AR 03 NAT SQ
60x120x1,2 / 24"x48"x¹/₂"



Pietra lavica AR 03 NAT SQ
30x120x1,2 / 12"x48"x¹/₂"



Pietra lavica AR 03 NAT SQ
60x60x1,05 / 24"x24"x¹/₂"



Pietra lavica AR 03 NAT SQ
30x60x1,05 / 12"x24"x¹/₂"



Pietra lavica AR 03 NAT SQ
45x45x1,05 / 18"x18"x¹/₂"














Pietra etrusca AR 04 NAT SQ
60x60x1,05 / 24"x24"x¹/₂"



Pietra etrusca AR 04 NAT SQ
30x60x1,05 / 12"x24"x¹/₂"



Pietra etrusca AR 04 NAT SQ
45x45x1,05 / 18"x18"x¹/₂"







IN92 Insert 1 NAT 60x60 / 24"x24"



IN93 Insert 2 NAT 60x60 / 24"x24"



IN94 Insert 3 NAT 60x60 / 24"x24"



IT46 Insert 4 NAT 60x60 / 24"x24"




IT47 Insert 5 NAT 60x60 / 24"x24"




IN95 Ang_Insert 1 NAT 60x60 / 24"x24"



IN96 Ang_Insert 2 NAT 60x60 / 24"x24"



IN97 Ang_Insert 3 NAT 60x60 / 24"x24"




IT40 Ang_Insert 4 NAT 60x60 / 24"x24"



IT41 Ang_Insert 5 NAT 60x60 / 24"x24"

inserti vetro per decoro "Insert" e "Ang_Insert":



- IR94 vetro trasparente opaco
- IR95 vetro blu opaco
- IR96 vetro rosso opaco
- IR93 vetro verde opaco
- IR91 vetro tessuto



IN86 Seventy_A 1 NAT 30x60 / 12"x24"



IN87 Seventy_A 2 NAT 30x60 / 12"x24"



IN88 Seventy_A 3 NAT 30x60 / 12"x24"



IT48 Seventy_A 4 NAT 30x60 / 12"x24"




IT49 Seventy_A 5 NAT 30x60 / 12"x24"



IN89 Seventy_B 1 NAT 30x60 / 12"x24"



IN90 Seventy_B 2 NAT 30x60 / 12"x24"



IN91 Seventy_B 3 NAT 30x60 / 12"x24"



IT50 Seventy_B 4 NAT 30x60 / 12"x24"



IT51 Seventy_B 5 NAT 30x60 / 12"x24"

pezzi per scatola
pieces for box
Stück pro Karton
pièces pour boîte
piezas por caja
Штук в коробке

Mattoncino



Belts



Insert



Angolo insert



Sixty



pezzi per scatola
pieces for box
Stück pro Karton
pièces pour boîte
piezas por caja
Штук в коробке

Seventy A / B



Bacchetta Vetro opaco



Bacchetta Vetro Tessuto



Bacchetta Alluminio



Inserti per "Insert" e "Ang. insert"



	45x45x1,05 18"x18"x¼"	30x60x1,05 12"x24"x¼"	60x60x1,05 24"x24"x¼"	30x120x1,2 12"x48"x½"	60x120x1,2 24"x48"x½"
	NAT SQ	NAT SQ	NAT SQ	NAT SQ	NAT SQ
 Pietra arria AR 01	●	●	●		
 Pietra serena AR 02	●	●	●	●	●
 Pietra lavica AR 03	●	●	●	●	●
 Pietra etrusca AR 04	●	●	●		
 Pietra imperiale AR 05	●	●	●	●	●
 Kg./mq. valore medio - average value Mittelwert - valeur moyen - valor medio кг/кв. м среднее значение	23,4	23,7	23,7	24,3	24,3
 pezzi per scatola - pièces for box Stück pro Karton - pièces pour boîte piezas por caja - Штук в коробке	5	6	3	2	2
 mq. scatola - mq. box - mq. Karton mq. boîte - mq. caja - кв.м в коробке	1,0125	1,08	1,08	0,72	1,44
 scatola/pallet - box/pallet - Karton/Pallet boîte/pallet - caja/pallet - коробок в палете	33	40	36	30	14
 mq./pallet	33,4125	43,2	38,88	21,6	20,16

	 Battiscopa* 8x45 / 3¼"x18"	 Gradino "A" 30x60 / 12"x24"	Jolly 1,2x29,8 / ½"x12"	Angolo jolly 1,2x1,2 / ½"x½"
	NAT	NAT	NAT	NAT
 Pietra arria AR 01	●	●	●	●
 Pietra serena AR 02	●	●	●	●
 Pietra lavica AR 03	●	●	●	●
 Pietra etrusca AR 04	●	●	●	●
 Pietra imperiale AR 05	●	●	●	●
 pezzi per scatola - pièces for box Stück pro Karton - pièces pour boîte piezas por caja - Штук в коробке	16	8	14	12

* Finitura a becco di civetta / One-round edge shaping / Ausführung mit Eckabrundung / Façonnage à bord rond / Acabado canto romo / Плитка с завалом

STANDARD EN 14411 - G

	CARATTERISTICHE TECNICHE TECHNICAL DATA TECHNISCHE DATEN CARACTERISTIQUES TECHNIQUES CARACTERÍSTICAS TÉCNICAS ТЕХНИЧЕСКИЕ ХАРАКТЕРИСТИКИ	NORMA STANDARD NORME NORME NORMA ЗНАЧЕНИЯ	VALORI PRESCRITTI DALLE NORME EN 14411 - G INTERNATIONAL STANDARDS EN 14411 - G INTERNATIONALE NORMWERTE EN 14411 - G VALEURS PREVUES PAR LES NORMES INTERNATIONALES EN 14411 - G VALORES PREVISTOS POR LAS NORMAS EN 14411 - G ПРЕДУСМОТРЕННЫЕ СТАНДАРТОМ EN 14411-G	*VALORE MEDIO MIRAGE MIRAGE AVERAGE VALUE MIRAGE MITTELWERT MIRAGE MOYEN MIRAGE VALOR MEDIO MIRAGE СРЕДНЕЕ ЗНАЧЕНИЕ
 LATI SIDES SEITEN COTES CANTOS РАЗМЕРЫ СТОРОН	CARATTERISTICHE DIMENSIONALI - SIZE CHARACTERISTICS MASSEIGENSCHAFTEN DETERMINATION DES CARACTERISTIQUES DIMENSIONELLES CARACTERÍSTICAS DIMENSIONALES РАЗМЕРНЫЕ ХАРАКТЕРИСТИКИ	EN ISO 10545-2	± 0,6% MAX	± 0,1%
 SPESSORE THICKNESS DICKE ÉPAISSEUR ESPESOR ТОЛЩИНА		EN ISO 10545-2	± 5,0% MAX	± 2%
 RETTILINEITÀ DEGLI SPIGOLI STRAIGHTNESS OF SIDES GERADLINIGKEIT DER KANTEN RECTITUDE DES ARÊTES RECTITUD DE LOS CANTOS КОСОУГОЛЬНОСТЬ		EN ISO 10545-2	± 0,5% MAX	± 0,0%
 ORTOGONALITÀ RECTANGULARITY RECHTWINKLIGKEIT PERPENDICULARITÉ ORTOGONALIDAD КРИВИЗНА СТОРОН		EN ISO 10545-2	± 0,6% MAX	± 0,2%
 PLANARITÀ SURFACE FLATNESS EBENFLÄCHIGKEIT PLANÉITÉ DE SURFACE PLANICIDAD КРИВИЗНА ЛИЦЕВОЙ ПОВЕРХНОСТИ		EN ISO 10545-2	± 0,5% MAX	± 0,1%
 ASSORBIMENTO D'ACQUA WATER ABSORPTION WASSERAUFNAHME ABSORPTION D'EAU ABSORCION DE AGUA ВОДОПОГЛОЩЕНИЕ		EN ISO 10545-3	≤ 0,5%	0,08%
 RESISTENZA ALLA FLESSIONE FLEXION RESISTANCE BIEGEFESTIGKEIT RESISTANCE A LA FLEXION RESISTENCIA A LOS GOLPES УДАРСТОЙКОСТЬ		EN ISO 10545-4	S≥ 700 N (<7,5 mm) S≥ 1.300 N (<7,5 mm) ≥ 35 N/mm²	S 2.937 N R 49,7 N/mm²
 RESISTENZA ALL'URTO IMPACT RESISTANCE STOSSFESTIGKEIT RESISTANCE AUX CHOCS RESISTENCIA A LOS GOLPES УДАРСТОЙКОСТЬ		EN ISO 10545-5	—	0,89
 RESISTENZA ALL'ABRASIONE ABRASION RESISTANCE ABRIEFESTIGKEIT RESISTANCE A L'ABRASION RESISTENCIA A LA ABRASION СТОЙКОСТЬ К ИСТИРАНИЮ		EN ISO 10545-6	≤ 175 mm³	133 mm³
 COEFFICIENTE DI DILATAZIONE TERMICA LINEARE COEFFICIENT OF LINEAR THERMAL-EXPANSION LINEARER WÄRMEAUSDEHNUNGSKOEFFIZIENT COEFFICIENT DE DILATATION THERMIQUE LINEAIRE COEFICIENTE DE DILATACIÓN TÉRMICA LINEAL КОЭФФИЦИЕНТ ЛИНЕЙНОГО ТЕРМИЧЕСКОГО РАСШИРЕНИЯ		EN ISO 10545-8	METODO DI PROVA DISPONIBILE TESTS METHOD AVAILABLE PRUEFUNG VERFUGBAR METHODE D'ESSAI DISPONIBLE METODO DE LABORATORIO DISPONIBLE ДОСТУПНЫЙ МЕТОД ИСПЫТАНИЯ	5,8x10 ⁻⁶ °C ⁻¹
 RESISTENZA AGLI SBALZI TERMICI RESISTANCE TO THERMAL SHOCKS BESTÄNDIGKEIT GEGEN TEMPERATURSCHWANKUNGEN RESISTANCE AUX CHOCS THERMIQUES RESISTENCIA A LOS CHOQUES TÉRMICOS СТОЙКОСТЬ К ПЕРЕПАДАМ ТЕМПЕРАТУРЫ		EN ISO 10545-9	METODO DI PROVA DISPONIBILE TESTS METHOD AVAILABLE PRUEFUNG VERFUGBAR METHODE D'ESSAI DISPONIBLE METODO DE LABORATORIO DISPONIBLE ДОСТУПНЫЙ МЕТОД ИСПЫТАНИЯ	NESSUN DANNO NO DAMAGE KEIN SCHADEN AUCUN DOMMAGE NINGUN DANO БЕЗ ПОВРЕЖДЕНИЙ
 RESISTENZA AL GELO FROST RESISTANCE FROSTBESTÄNDIGKEIT RESISTANCE AU GEL RESISTENCIA AL HIELO МОРОЗОСТОЙКОСТЬ		EN ISO 10545-12	NESSUN DANNO NO DAMAGE KEIN SCHADEN AUCUN DOMMAGE NINGUN DANO БЕЗ ПОВРЕЖДЕНИЙ	NESSUN DANNO NO DAMAGE KEIN SCHADEN AUCUN DOMMAGE NINGUN DANO БЕЗ ПОВРЕЖДЕНИЙ
 RESISTENZA ALL'ATTACCO CHIMICO RESISTANCE TO CHEMICALS CHEMIKALIENBESTÄNDIGKEIT RESISTANCE A L'ATTAQUE CHIMIQUE RESISTENCIA QUÍMICA ХИМИЧЕСКАЯ СТОЙКОСТЬ		EN ISO 10545-13	UB MIN. UB MIN. UB MIN. UB MIN. UB MIN.	UA ULA UHA
 RESISTENZA ALLE MACCHIE RESISTANCE TO STAINS FLECKENBESTÄNDIGKEIT RESISTANCE AUX TACHES RESISTENCIA A LAS MANCHAS УСТОЙЧИВОСТЬ К ПЯТНООБРАЗОВАНИЮ		EN ISO 10545-14	METODO DI PROVA DISPONIBILE TESTS METHOD AVAILABLE PRUEFUNG VERFUGBAR METHODE D'ESSAI DISPONIBLE METODO DE LABORATORIO DISPONIBLE ДОСТУПНЫЙ МЕТОД ИСПЫТАНИЯ	5
 CESSIONE DI PIOMBO E CADMIO LEAD AND CADMIUM DISCHARGE ABGABE VON BLEI UND CADMIUM PERTE DE PLOMB ET CADMIUM CESIÓN DE PLOMO Y CADMIO ВЫДЕЛЕНИЕ СВИНЦА И КАДМИЯ		EN ISO 10545-15	METODO DI PROVA DISPONIBILE TESTS METHOD AVAILABLE PRUEFUNG VERFUGBAR METHODE D'ESSAI DISPONIBLE METODO DE LABORATORIO DISPONIBLE ДОСТУПНЫЙ МЕТОД ИСПЫТАНИЯ	< AL LIMITE DI RILEVAMENTO < THAN INSTRUMENT LIMIT < UNMESSBARES WERT < LIMITE DE L'INSTRUMENT < LIMITE DEL INSTRUMENTO < НА ПРЕДЕЛЕ ОПРЕДЕЛИМОСТИ
 SCIVOLOSITÀ SKID RESISTANCE RUTSCHWERT GLEISSANCE ADHERENCIA СКОЛЬЗКОСТЬ		DM 236/89 BCRA	> 0,40	> 0,40

* COME DA CERTIFICATO NR. 380/2006, 7/2006, 453/2006, 25/2006, 254/2006.
ACCORDING TO TEST REPORT NR. 380/2006, 7/2006, 453/2006, 25/2006, 254/2006.
LAUT ZEUGNISS NR. 380/2006, 7/2006, 453/2006, 25/2006, 254/2006.
SELON LE CERTIFICAT NR. 380/2006, 7/2006, 453/2006, 25/2006, 254/2006.
COMO RESULTA POR EL CERTIFICADO NR. 380/2006, 7/2006, 453/2006, 25/2006, 254/2006.
В СООТВЕТСТВИИ С CERTИФИКАТОМ NR. 380/2006, 7/2006, 453/2006, 25/2006, 254/2006.